

IMPERIA POLYESTER LUXURY WOOD FINISH

TECHNICAL DATA

SL. No.	Parameter	Specifications
01.	Appearance	Clear yellowish liquid
02.	Viscosity @ 30°C	18 to 22 Secs
03.	Specific Gravity @ 30°C	1.07 +/- 0.01
04.	Pot-Life	10 to 15 minutes
05.	Application	Conventional Spray
06.	Surface Dry time @ 30°C	1 Hr Max
07.	Sanding Dry time @ 30°C	3 Hrs Max
08.	Gloss @ 60° Gloss Head	99 to 100
09.	Gloss @ 60° Gloss Head	98 to 99
10.	DOI (Image clarity)	Should be highly transparent & see-through visibility of Wood grains.
11.	Coverage	0.5-0.9 Sq.m/L depending upon the thickness required.

