

NIPPON PAINT SATIN GLO PRIME

A Luxury Interior Emulsion is based on pure Acrylic emulsion formulated to impart High sheen to decorate interior walls. It possesses excellent washability and stain resistance to keep the walls beautiful for long. It contains low VOC ensuring safe and healthy interiors. Its anti-bacterial property provides proven protection against bacteria and also contains low VOC ensuring safe and healthy interiors.

'IN GLO

GREEN ASSURED



PRODUCT FEATURES



High Sheen Finish Gives rich luxurious look and feel to walls



Stain-resistant Stain free clean walls resulting in a healthy environment



Anti-bacterial

Keeps the walls hygienic. It reduces the chance of picking up allergies and keeps residents healthy.



Low VOC

Healty interiors- ensure that home owners can occupy the house immediately after painting.











TECHNICAL DETAILS

Bases	:	White & Base 4, Base 3, Base 2, Base 1, Red & Yellow Base
Colour Range	:	Please refer to Nippon Paint shade card and fan decks
Finish	:	High Sheen Finish
Dry Time	:	To Touch: 30 minutes To Recoat: 4-6 Hours
Gloss level	:	60° Head: 45- 55 units
Clean up solvent	:	Clean, potable water
Stability of diluted paint	:	24 Hours
Shelf life	:	3 Years from the date of manufacture in origional tightly
		closed containers .
Dilution	:	Upto 40% by volume with clean potable water.
		Stir well before use. Upto 20% by volume with clean
		potable watter for dark shades.

Coverage:



SATIN GLO PRIME

240-260 sq ft/litre/coat & 110-130 sq ft/litre/2 coats

(Actual coverage is dependant on the substrate condition, surface porosity, method of application)

HOW TO APPLY

Surface Preparation:



Keep surface clean & dry. Remove dust, dirt, grease and any flaking paint from the surface and sand to smooth.Ensure there is no fungus or moisture on the wall.

Application:

Brush: Dilute both 1st and 2nd coats with 40% water Dilute both 1st and 2nd coats with 40% water Roller: Conventional Spray: Dilute both 1st and 2nd coats with 40% water

SAFETY AND ENVIRONMENT

During Painting:

Always work in a well ventilated area. Wear appropriate attire, especially gloves and eye protection gear. Avoid contact with skin as it may cause irritation.

Cleaning:

Clean all equipments with clean water immediately after use.

Safety Instructions:

In the case of eye contact, rinse immediately with water and seek immediate medical treatment. To remove paint from skin, use soap and water or appropriate cleanser. In the event of spillage, contain and collect spilt paint by using sand or earth.

Precautions:

Avoid painting when the temperature is below 10 degrees Celsius. Painting is not recommended if the moisture content and alkalinity of the walls is high. Moisture content of the walls should be below 16% (measured by Protimeter) and alkalinity of the wall should be below pH-9. Relative humidity should be below 85%. Painting on a newly plastered wall is recommended after 12 weeks of curing.

Process:

Primer

Nippon Paint

Multi-Purpose

Interior Primer

Apply 1 coats

Allow it to dry

for 6-8 hours

Wall Sealer/



Putty Nippon Paint Acrylic Wall Putty

Apply 1-2 coats

Allow it to dry for 12-18 hours





Nippon Paint

Satin Glo Prime

Primer Nippon Paint Multi-Purpose Wall Sealer/ **Interior Primer** Apply 1 coats

Allow it to dry

for 6-8 hours

Apply 2-3 coats Allow it to dry

for 4-6 hours

Storage:

Store paint in a cool, dry and well ventilated place away from heat sources, flammables or direct sunlight. Keep container tightly closed in a secure, upright position. Do not store near food, drink or animal feed. Keep out of reach of children. Do not dispose of unwanted paint into drains, water sources or open sewers. To dispose safely, pour unwanted paint onto old newspapers and let dry before placing in a proper waste receptacle.

Disposal Information:

Disposal of any paint waste & containers in accordance with applicable Environment (Protection) Act 1986 under the Hazardous Wastes (Management & Handling) rules 1989.

Environment:

Does not contain any added lead, mercury or chromium compunds. Lead content does not exceed 90 parts per million.

